



# Test Report

Report No.: CX/2017/90023

Date: 2017/09/21

RAYTAC CORPORATION  
5F, NO. 3, JIANKANG ROAD, ZHONGHE DISTRICT, NEW TAIPEI CITY 23586, TAIWAN

The following sample(s) was/were submitted and identified by/on behalf of the applicant as :

Sample Submitted By : RAYTAC CORPORATION  
Sample Description : Bluetooth Module  
Style/Item No. : MDBT42V-P Series  
Sample Receiving Date : 2017/09/06  
Testing Period : 2017/09/06 to 2017/09/20

=====  
**Test Result(s)** : Please refer to next page(s).

**Conclusion** : Based upon the performed tests on submitted samples, the test results comply with the limits of RoHS Directive 2011/65/EU and amending Directive (EU) 2015/863.

  
Wendy Wei, Supervisor  
Signed for and on behalf of  
SGS TAIWAN LTD.  
Chemical Laboratory - Taipei



This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Termse-Document.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

## Test Report

Report No.: CX/2017/90023

Date: 2017/09/21

### 1. Material Fraction Composition

Table 1 The results of XRF screening and chemical test



No.	Type of Components	Description	Figure	MDL Category	X-ray Screening		UV	ICP-AES	GC-MS	Other Chemical Test	Note
					Element	Data	Cr (VI)	Pb/Cd/Hg	PBB/PBDE		
1	PCBA	1.1		Composite Material	Pb	---	n.d.	21.0	n.d.	Refer to table 4	Refer to table 2
					Cd	---		n.d.			
					Hg	---		n.d.			
					Cr	---					
					Br	---					
					Cr(VI)						
					PBB						
	PBDE										
	SILVERY METALLIC COVER	1.2		Metals	Pb	n.d.	---	---	---	---	
					Cd	n.d.		---			
					Hg	n.d.		---			
					Cr	n.d.					
					Br	n.d.					
					Cr(VI)						
PBB											
PBDE											

Table 2 The test results on the PCBA (CX/2017/90023-1.1) by point analysis (Unit: mg/kg)



Point Analysis	No.	Figure	Material	X-ray Screening		
			Type	Element	Data	Note
	1		Composite Material	Pb	n.d.	Refer to No.1 in Table 3
				Cd	n.d.	
				Hg	n.d.	
				Cr	n.d.	
				Br	35800	

Table 3 The confirming test results for point analysis on PCBA (Unit: mg/kg)



Type of Components	Description		Figure	MDL Category	Substance	UV	ICP-AES	GC-MS	Note
						Cr (VI)	Pb/Cd/Hg	PBB/PBDE	
No.1.1 	1	RAW PCB		Composite Material	Pb		---		
Cd					---				
Hg					---				
Cr									
Br									
Cr(VI)					---				
PBB						n.d.			
PBDE						n.d.			

Table 4 The test results of Phthalates (Unit: mg/kg)

Test Item (s):	Method	MDL	Result
			1.1
BBP (Butyl Benzyl phthalate) (CAS No.: 85-68-7)	With reference to IEC 62321-8 (2017). Analysis was performed by GC/MS.	50	n.d.
DBP (Dibutyl phthalate) (CAS No.: 84-74-2)		50	n.d.
DEHP (Di- (2-ethylhexyl) phthalate) (CAS No.: 117-81-7)		50	n.d.
DIBP (Di-isobutyl phthalate) (CAS No.: 84-69-5)		50	n.d.



# Test Report

Report No.: CX/2017/90023

Date: 2017/09/21

Test Item	MDL (mg/kg)				XRF screening threshold	Test method
	Category Element	Polymers	Composite Material	Metals		
XRF (X-ray fluorescence)	Pb	50	100	100	500	With reference to IEC 62321-3-1 (2013)
	Cd	50	50	50	50	
	Hg	50	100	100	500	
	Cr	50	100	100	500	
	Br	50	100	n.a.	250	

Test Item (s)	Test method	MDL	Unit
Cr(VI)	With reference to IEC 62321-7-2 (2017) and performed by UV-VIS. (For Polymers and Electronics)	8	mg/kg
	With reference to IEC 62321-7-1 (2015) and performed by UV-VIS. (For Coatings on Metals) (#2)	0.1	µg/cm <sup>2</sup>
Pb/Cd	With reference to IEC 62321-5 (2013) and performed by ICP-AES.	2	mg/kg
Hg	With reference to IEC 62321-4 (2013) and performed by ICP-AES.	2	mg/kg

Test Item (s)	Unit	Method	MDL (mg/kg)	
<b>PBBs</b>				
Monobromobiphenyl	mg/kg	With reference to IEC 62321-6 (2015) and performed by GC/MS.	5	
Dibromobiphenyl	mg/kg		5	
Tribromobiphenyl	mg/kg		5	
Tetrabromobiphenyl	mg/kg		5	
Pentabromobiphenyl	mg/kg		5	
Hexabromobiphenyl	mg/kg		5	
Heptabromobiphenyl	mg/kg		5	
Octabromobiphenyl	mg/kg		5	
Nonabromobiphenyl	mg/kg		5	
Decabromobiphenyl	mg/kg		5	
<b>PBDEs</b>				
Monobromodiphenyl ether	mg/kg		5	
Dibromodiphenyl ether	mg/kg		5	
Tribromodiphenyl ether	mg/kg		5	
Tetrabromodiphenyl ether	mg/kg	5		
Pentabromodiphenyl ether	mg/kg	5		
Hexabromodiphenyl ether	mg/kg	5		
Heptabromodiphenyl ether	mg/kg	5		
Octabromodiphenyl ether	mg/kg	5		
Nonabromodiphenyl ether	mg/kg	5		
Decabromodiphenyl ether	mg/kg	5		

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at <http://www.sgs.com/en/Terms-and-Conditions.aspx> and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at <http://www.sgs.com/en/Terms-and-Conditions/Termse-Documents.aspx>. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of client's instruction, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced, except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Unless otherwise stated the results shown in this test report refer only to the sample(s) tested.

1. mg/kg = ppm
2. MDL = Method detection limit
3. n.d. = not detected or lower than MDL
4. "---" = not conducted
5. n.a. = not applicable
6. " - " = Not Regulated
7. The XRF result of Br for metal sample is conducted from semi-quantitative method of polymer. If the Br result is shown as n.d., the reading will be less than 100ppm.
8. (#2):
  - a. The sample is positive for Cr(VI) if the Cr(VI) concentration is greater than 0.13  $\mu\text{g}/\text{cm}^2$ .  
The coating is considered to contain Cr(VI).
  - b. The sample is negative for Cr(VI) if Cr(VI) is n.d. (concentration less than 0.10  $\mu\text{g}/\text{cm}^2$ ).  
The coating is considered a non-Cr(VI) based coating.
  - c. The result between 0.10  $\mu\text{g}/\text{cm}^2$  and 0.13  $\mu\text{g}/\text{cm}^2$  is considered to be inconclusive - unavoidable coating variations may influence the determination.

9. Magnetic samples can not be located on test position and there are breakdown risks on XRF equipment. Therefore, this kind of sample will be conducted chemical test directly.
10. If the test result by EDXRF analysis is greater than XRF screening threshold, the test sample should be further conducted by chemical test.

Mark	Description of Mark
*1	The sample weight is not enough to conduct chemical tests.
*2	The item is exempted from EU RoHS directive.
--*2	The item might be exempted from EU RoHS directive.
*3	The result was retested after regetting the same sample from client.
*4	The sample is provided separately from the client.
*5	Adopting modified IEC 62321-7-1(2015), due to the test area less than 25 $\text{cm}^2$
*6	The test item was tested by dry base.
*7	This sample follows requirement of client to conduct directly chemical tests.